

Suspension Polyvinylchloride (PVC-S)

S-6669PJ
Bashkir Soda Company JSC., Russia

PROPERTIES

Description	White consistent powder. GOST 14332-78; TU 2212-186-00203312-98; STO 00203312-006-2012	
Applications	Window and door profiles, siding.	
K-value		66-68
Amount of impurities and foreign objects	ea., no more	6
Number of "fish eye" transparent points on 0.1 cm³ of film	ea., no more	6
Bulk density	g/cm ³	0,56 +/-0,02
Residue after sieving on a sieve with mesh:		
№0315	%, no more	Absence
№0063	%, not less than	95
Flowability	s, no more	Not rated
Plasticizer saturation mass	g/100g PVC, not less than	20
Thermal stability, at 160°C	min, not less than	20
Mass fraction of moisture and volatile substances	%, no more	0,3
Mass fraction of the vinyl chloride	mln ⁻¹ , no more	1
Volume resistivity at 20 °C after keeping in distilled water for 2 h	Ohm*cm, not less than	5*10¹³

These are typical properties: not to be construed as specification.