

**Ethylene-Vinyl Acetate Copolymer  
(EVA)****VZ732****UBE-MARUZEN POLYETHYLENE Co., Japan****PROPERTIES**

<b>Additives</b>	Additive-free.		
<b>Features</b>	High transparency, stretchability, flexibility.		
<b>Applications</b>	Transparent sheet, foamed product, modifier.		
<b>MFR</b>	g/10min	<b>6</b>	ASTM D1238
<b>Density</b>	kg/m <sup>3</sup>	<b>949</b>	ASTM D1505
<b>VA</b>	%	<b>26</b>	Метод UBE
<b>Melting point</b>	°C	<b>75</b>	Метод UBE
<b>Tensile strength</b>	MPa	<b>21</b>	ASTM D638
<b>Tensile elongation</b>	%	<b>800</b>	ASTM D638
<b>Flexural strength(Olsen)</b>	MPa	<b>24</b>	ASTM D747
<b>Hardness</b>	(HDA)	<b>88</b>	ASTM D2240
<b>Vicat softening point</b>	°C	<b>42</b>	ASTM D1525
<b>Brittle temperature</b>	°C	<b>&lt;-75</b>	ASTM D746

*These are typical properties: not to be construed as specification.*