

Limited

Tel: +7 (495) 747 92 61/63, +7 (499) 133 37 83

Fax: +7 (495) 747 92 69

e-mail: info@transchem.ru, transchem@mail.ru web: www.transchem.ru

> Polypropylene homopolymer (PP)

Balen 01270 Ufaorgsintez, Russian Federation

PROPERTIES

Balen 01270 is polypropylene homopolymer. Has high resistance to thermo-oxidative aging.

Applications Textured and not textured filament, thin staple fibers, products, food contact products, toys.

Melt Flow Rate (230 °C/2.16 kg)	g/10 min	22-30	GOST 11645 / ASTM D1238
Tensile Stress at Yield (not less than)	МРа	not regulated	
Elongation at Yield (not less than)	%	not regulated	
Flex modulus (5 мм/мин) (not less than)	МРа	1200	ASTM D790
ESCR (150 °C) (not less than)	hr	360	ISO 4577
Mass fraction of isotactic fraction (not less than)	%	94	

These are typical properties: not to be construed as specification.

